

543

3 MIL UNSUPPORTED TRANSFER FILM

DESCRIPTION: A 3 mil (75 micron) unsupported acrylic transfer film.

APPLICATIONS: A high performance acrylic transfer tape designed for metal to metal and plastic to metal applications. The 3 mil (75 micron) thickness allows for extra conformability. Good temperature and UV resistance. It also, has excellent resistance to high temperatures up to 350°F (177°C).

TECHNICAL DATA

	<u>Imperial</u>	<u>Metric</u>
Thickness (exclusive of liner):	3.0 mil (.001 in)	0.076 mm
Adhesion:		
Immediate Peel(PSTC-1):	70.0 oz/inch width	20.0 N/2.5 cm
Ultimate Peel:	90 oz/inch width	25.3 N/2.5 cm
Shear (PSTC-7A):48 hrs @	2.2 psi	15.2 kPa
Hot Shear (PSTC-7C):1 hr @	212°F @ 2.2 psi	100°C @ 15.2 kPa
Tensile:	N/A	
Elongation:	N/A	
Temperature Resistance:	350°F	177°C
Minimum Application		
Temperature:	N/A	
Release Liner:	80 lb bleached kraft	130 GSM

IMPORTANT INFORMATION:

The physical properties listed above are typical test results obtained from a series of laboratory tests and should not be used for the purpose of writing specifications. Before using the product, user shall determine the suitability of the product for his/her intended use; and user assumes all risks and liabilities in connection therewith. All test procedures used are in accordance with ASTM and PSTC methods.

4/2/98